



(11)Publication number:

06-200149

(43)Date of publication of application: 19.07.1994

(51)Int.CI.

CO8L 75/00 CO9C 3/10 CO9D 5/00 CO9D 11/02 CO9D 17/00

C09D175/00 // C08G 18/00 C08G 18/80

(21)Application number: 05-250079

(71)Applicant: SANYO CHEM IND LTD

(22)Date of filing:

09.09.1993

(72)Inventor: TANAKA MASAHIKO

OISHI HIROSHI

(30)Priority

Priority number: 04283765

Priority date : 28.09.1992

Priority country: JP

(54) WATER-BASED PIGMENT DISPERSION

(57)Abstract:

PURPOSE: To provide the subject dispersion composed of a pigment and a water-based urethane resin and having improved dispersion stability of the pigment and remarkably improved water-resistance of coating film compared with conventional dispersion when used as a colorant for water-paint or water-based printing ink.

CONSTITUTION: The objective dispersion is composed of (A) a pigment and (B) a water-based urethane resin and contains 0.1–10 pts.wt. of the component B based on 1 pt.wt. of the component A. The component B is produced preferably by reacting an active hydrogen-containing compound such as a 2–6C branched or straight-chain alkanediol adipate and/or phthalate diol or 1,4– butanediol with a compound having active hydrogen and hydrophilic group such as α α -diol propionic acid and an organic polyisocyanate such as 2,4– tolylene diisocyanate, subjecting the obtained prepolymer having hydrophilic group to a treatment to form anion or cation and dissolving the product while extending the chain with water and/or a polyamine.

LEGAL STATUS

[Date of request for examination]

15.07.1994

[Date of sending the examiner's decision of

rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or

application converted registration]

[Date of final disposal for application]

3347840

[Date of registration]

[Patent number]

06.09.2002

[Number of appeal against examiner's decision of rejection]
[Date of requesting appeal against examiner's decision of rejection]
[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office